

成形材料試験成績表

平成29年12月度



株式会社 未来樹



〒187-0043 東京都小平市学園東町1丁目7番14号
TEL:042-346-1100 FAX:042-346-2020

成形材料名: ポリエチレン

試験項目	試験方法	単位	規格値	試験値
密度	JIS K 7112	kg/m ³	942 以上	965
メルトフローレート	JIS K 7210	g/10min	1.5 以上 6.0 未満	5.2
引張降伏強さ	JIS K 7161	MPa	19.61 以上	27.91
デュロメータD硬さ	JIS K 7215	H _D D	60 以上	64
ビカト軟化点	JIS K 7206	°C	105 以上	127

[備考] 本表は、材料メーカーの報告によるもので、当社製品の成形材料です。

K形スピーサ 試験成績書

平成 29年 12月度




株式会社 未来樹



〒187-0043 東京都小平市学園東町1丁目7番14号

TEL:042-346-1100 FAX:042-346-2020



項目 種類	外 観 形 状	K1			K2			K3			K4			全長		
		寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
旧K30-3-3	良	20.0	1.0	19.2	11.0	0.5	11.1	18.0	0.5	17.9	20.0	1.0	20.6	29.0	1.0	29.0
K30-3-3	良	30.0	1.0	29.8	11.0	0.5	11.0	18.0	0.5	17.8	20.0	1.0	20.8	29.0	1.0	28.8
旧K35-3-3	良	20.0	1.0	19.2	11.0	0.5	11.0	22.0	1.0	21.7	20.0	1.0	20.8	33.0	1.0	32.7
K35-3-3	良	30.0	1.0	29.8	11.0	0.5	11.0	22.0	1.0	22.0	20.0	1.0	20.8	33.0	1.0	33.0
旧K40-3-3	良	20.0	1.0	20.0	11.0	0.5	11.3	27.0	1.0	26.9	20.0	1.0	20.6	38.0	1.0	38.2
K40-3-3	良	30.0	1.0	29.9	11.0	0.5	11.5	27.0	1.0	27.0	20.0	1.0	20.5	38.0	1.0	38.5
K40-5-4	良	30.0	1.0	30.1	15.0	0.5	15.1	23.0	1.0	22.9	19.0	0.5	18.9	38.0	1.0	38.0
旧K45-3-3	良	20.0	1.0	19.9	11.0	0.5	10.9	32.0	1.0	31.9	20.0	1.0	20.5	43.0	2.0	42.8
K45-3-3	良	30.0	1.0	30.0	11.0	0.5	11.2	32.0	1.0	32.1	20.0	1.0	20.6	43.0	2.0	43.3
K45-5-4	良	30.0	1.0	30.1	15.0	0.5	15.3	28.0	1.0	27.9	19.0	0.5	19.4	43.0	2.0	43.2
K45-6-4	良	30.0	1.0	29.9	15.0	0.5	14.9	29.0	1.0	29.3	20.0	1.0	20.2	44.0	2.0	44.2
旧K50-4-4	良	20.0	1.0	19.7	15.0	0.5	15.4	33.0	1.0	32.3	20.0	1.0	20.2	48.0	2.0	47.7
K50-4-4	良	30.0	1.0	30.0	15.0	0.5	15.5	33.0	1.0	32.4	20.0	1.0	20.3	48.0	2.0	47.9
K50-5-4	良	30.0	1.0	30.0	15.0	0.5	15.1	33.0	1.0	32.7	19.0	0.5	19.1	48.0	2.0	47.8
K50-6-4	良	30.0	1.0	30.1	15.0	0.5	15.1	33.0	1.0	33.4	20.0	1.0	20.1	48.0	2.0	48.5
K50-6-6S	良	16.0	0.5	15.5	12.0	0.5	11.8	35.0	1.0	35.8	17.0	0.5	16.7	47.0	2.0	47.6
旧K55-5-4	良	20.0	1.0	19.2	15.0	0.5	14.9	37.0	1.0	37.0	20.0	1.0	20.7	52.0	2.0	51.9
K55-5-4	良	30.0	1.0	29.8	15.0	0.5	14.9	37.0	1.0	37.0	20.0	1.0	20.4	52.0	2.0	51.9
K55-6-4	良	30.0	1.0	29.9	15.0	0.5	15.0	38.0	1.0	38.2	20.0	1.0	20.3	53.0	2.0	53.2
K60-6-4	良	30.0	1.0	30.0	15.0	0.5	15.5	43.0	2.0	43.3	20.0	1.0	20.1	58.0	2.0	58.8
K60-6-6JR	良	30.0	1.0	29.8	17.0	0.5	16.7	41.0	2.0	40.7	29.0	1.0	28.4	58.0	2.0	57.4
K60-6-6S	良	17.0	0.5	17.2	11.0	0.5	11.3	45.0	2.0	43.6	17.0	0.5	16.6	56.0	2.0	54.9
K65-6-4	良	30.0	1.0	29.9	15.0	0.5	14.9	48.0	2.0	48.2	20.0	1.0	20.2	63.0	2.5	63.1
K70-6-6	良	30.0	1.0	29.9	15.0	0.5	14.8	53.0	2.0	54.2	20.0	1.0	20.1	68.0	2.5	69.0
K70-6-6P	良	25.0	1.0	24.7	16.0	0.5	16.5	51.0	2.0	50.9	27.0	1.0	26.5	67.0	2.5	67.4
K70-10-10	良	18.0	0.5	17.7	9.0	0.5	9.4	58.0	2.0	57.7	22.0	1.0	22.1	67.0	2.5	67.1
K74-6-6L	良	30.0	1.0	30.8	6.0	0.5	6.3	59.0	2.0	59.2	20.0	1.0	19.5	65.0	2.5	65.5
K80-4-4L	良	30.0	1.0	30.0	6.0	0.5	6.4	57.0	2.0	56.6	22.0	1.0	21.6	63.0	2.5	63.0
K80-6-6	良	30.0	1.0	29.1	15.0	0.5	15.0	63.0	2.5	64.1	20.0	1.0	19.8	78.0	2.5	79.1
K80-6-6L	良	30.0	1.0	31.0	6.0	0.5	6.4	65.0	2.5	66.0	20.0	1.0	19.7	71.0	2.5	72.4
旧K80-10-6	良	20.0	1.0	20.0	8.0	0.5	8.3	69.0	2.5	68.6	10.0	0.5	9.5	77.0	2.5	76.9

項目 種類	外觀 形状	K1			K2			K3			K4			全長		
		寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
K80-10-6	良	30.0	1.0	30.8	16.0	0.5	15.6	62.0	2.5	62.6	30.0	1.0	30.2	78.0	2.5	78.2
K80-10-10	良	18.0	0.5	18.0	9.0	0.5	9.4	68.0	2.5	67.7	22.0	1.0	22.0	77.0	2.5	77.1
K85-4-4L	良	30.0	1.0	30.1	6.0	0.5	6.4	64.0	2.5	63.8	22.0	1.0	21.6	70.0	2.5	70.2
旧K85-10-6	良	20.0	1.0	20.0	10.0	0.5	10.2	73.0	2.5	72.8	10.0	0.5	9.5	83.0	2.5	83.0
K85-10-6	良	30.0	1.0	29.7	16.0	0.5	16.0	67.0	2.5	67.7	30.0	1.0	30.2	83.0	2.5	83.7
K90-4-4L	良	30.0	1.0	30.1	6.0	0.5	6.4	69.0	2.5	68.6	22.0	1.0	21.7	75.0	2.5	75.0
K90-4-4S	良	30.0	1.0	29.6	33.0	1.0	32.7	55.0	2.0	55.3	27.0	1.0	26.9	88.0	2.5	88.0
K90-6-4	良	30.0	1.0	29.7	15.0	0.5	14.7	70.0	2.5	70.7	23.0	1.0	22.7	85.0	2.5	85.4
K90-10-6H	良	30.0	1.0	31.0	16.0	0.5	15.5	69.0	2.5	69.9	30.0	1.0	30.2	85.0	2.5	85.4
K90-10-6	良	20.0	1.0	19.3	15.0	0.5	15.5	70.0	2.5	70.8	23.0	1.0	23.2	85.0	2.5	86.3
K90-10-6L	良	30.0	1.0	29.4	15.0	0.5	15.1	70.0	2.5	70.7	23.0	1.0	23.5	85.0	2.5	85.8
K95-4-4S	良	30.0	1.0	29.5	33.0	1.0	32.5	60.0	2.5	60.1	27.0	1.0	26.8	93.0	3.0	92.6
K95-6-6L	良	30.0	1.0	30.8	6.0	0.5	6.4	75.0	2.5	75.6	20.0	1.0	19.5	81.0	2.5	82.0
K95-6-6S	良	30.0	1.0	30.0	17.0	0.5	16.8	76.0	2.5	75.7	29.0	1.0	28.5	93.0	3.0	92.5
K95-10-6	良	30.0	1.0	29.7	20.0	1.0	20.1	70.0	2.5	70.7	23.0	1.0	22.5	90.0	3.0	90.8
K95-10-6H	良	30.0	1.0	30.7	16.0	0.5	15.7	74.0	2.5	75.8	30.0	1.0	30.1	90.0	3.0	91.5
K95-10-10	良	30.0	1.0	30.1	20.0	1.0	19.8	70.0	2.5	69.6	25.0	1.0	24.3	90.0	3.0	89.4
K95-13-6	良	22.0	1.0	22.0	20.0	1.0	19.6	70.0	2.5	70.2	23.0	1.0	23.3	90.0	3.0	89.8
K95-13-6L	良	30.0	1.0	30.0	20.0	1.0	19.7	70.0	2.5	71.2	23.0	1.0	23.2	90.0	3.0	90.9
K95-13-13	良	30.0	1.0	29.9	18.0	0.5	18.5	72.0	2.5	71.1	23.0	1.0	23.2	90.0	3.0	89.6
K100-10-6H	良	30.0	1.0	30.9	16.0	0.5	15.7	79.0	2.5	79.0	30.0	1.0	29.9	95.0	3.0	94.7
K100-10-6P	良	25.0	1.0	24.5	15.0	0.5	15.5	81.0	2.5	80.3	25.0	1.0	24.4	96.0	3.0	95.8
K100-10-10	良	30.0	1.0	30.0	19.0	0.5	18.5	76.0	2.5	76.6	24.0	1.0	23.7	95.0	3.0	95.1
K100-13-10	良	22.5	1.0	22.3	15.0	0.5	14.6	75.0	2.5	75.9	41.5	2.0	41.6	90.0	3.0	90.5
K100-13-13	良	22.0	1.0	21.8	15.0	0.5	15.5	80.0	2.5	79.3	23.0	1.0	22.4	95.0	3.0	94.8
K105-6-6H	良	25.0	1.0	24.7	17.0	0.5	16.6	83.0	2.5	83.0	26.0	1.0	26.3	100.0	3.0	99.6
K110-4-4S	良	30.0	1.0	29.5	43.0	2.0	42.9	65.0	2.5	64.9	27.0	1.0	26.7	108.0	3.0	107.8
K110-6-6H	良	25.0	1.0	24.7	17.0	0.5	16.5	88.0	2.5	88.0	27.0	1.0	26.2	105.0	3.0	104.5
K110-10-6	良	30.0	1.0	29.8	20.0	1.0	19.4	85.0	2.5	85.5	23.0	1.0	22.9	105.0	3.0	104.9
K110-10-6H	良	30.0	1.0	31.0	16.0	0.5	15.8	89.0	2.5	89.1	30.0	1.0	30.2	105.0	3.0	104.9
K110-10-10	良	30.0	1.0	30.8	20.0	1.0	19.7	82.0	2.5	81.2	24.0	1.0	24.3	102.0	3.0	100.9
K110-13-6	良	22.0	1.0	21.7	20.0	1.0	19.8	85.0	2.5	85.0	23.0	1.0	23.0	105.0	3.0	104.8
K110-13-6L	良	30.0	1.0	29.8	20.0	1.0	19.8	85.0	2.5	84.6	23.0	1.0	23.2	105.0	3.0	104.4
K110-13-13	良	30.0	1.0	30.2	20.0	1.0	19.9	84.0	2.5	83.9	23.0	1.0	23.0	104.0	3.0	103.8
K115-6-6H	良	25.0	1.0	24.6	17.0	0.5	16.5	93.0	3.0	93.3	27.0	1.0	26.3	110.0	3.0	109.8
K120-6-6H	良	25.0	1.0	24.7	17.0	0.5	16.6	98.0	3.0	97.9	27.0	1.0	26.5	115.0	3.0	114.5
K120-10-6H	良	30.0	1.0	30.8	16.0	0.5	15.7	99.0	3.0	99.0	30.0	1.0	30.1	115.0	3.0	114.7
K120-10-10	良	30.0	1.0	30.6	20.0	1.0	19.9	95.0	3.0	95.0	24.0	1.0	24.1	115.0	3.0	114.9
K120-13-10	良	22.5	1.0	22.7	15.0	0.5	14.9	95.0	3.0	95.5	41.5	2.0	41.5	110.0	3.0	110.4
K120-13-13	良	30.0	1.0	30.0	20.0	1.0	19.7	95.0	3.0	96.0	23.0	1.0	23.4	115.0	3.0	115.7
K125-4-4S	良	30.0	1.0	29.7	48.0	2.0	47.3	75.0	2.5	74.4	27.0	1.0	26.8	123.0	3.0	121.7
K125-10-6	良	30.0	1.0	29.9	20.0	1.0	20.1	100.0	3.0	99.1	23.0	1.0	22.6	120.0	3.0	119.2
K125-13-6	良	22.0	1.0	21.9	20.0	1.0	19.6	100.0	3.0	99.3	23.0	1.0	23.3	120.0	3.0	118.9
K125-13-6L	良	30.0	1.0	29.9	20.0	1.0	19.9	100.0	3.0	99.9	23.0	1.0	23.5	120.0	3.0	119.8
K130-10-10	良	30.0	1.0	30.4	20.0	1.0	20.0	105.0	3.0	105.4	25.0	1.0	24.3	125.0	3.0	125.4
K130-13-10	良	22.5	1.0	22.3	15.0	0.5	14.6	105.0	3.0	104.9	41.5	2.0	41.4	120.0	3.0	119.5
K130-13-13	良	30.0	1.0	30.2	20.0	1.0	19.9	105.0	3.0	105.6	23.0	1.0	23.4	125.0	3.0	125.5
K135-10-6H	良	30.0	1.0	29.5	16.0	0.5	15.7	114.0	3.0	113.1	30.0	1.0	29.4	130.0	3.0	128.8
K145-10-6H	良	30.0	1.0	30.1	16.0	0.5	15.8	124.0	3.0	123.9	30.0	1.0	29.5	140.0	3.0	139.7
K150-10-10	良	30.0	1.0	30.7	20.0	1.0	20.3	125.0	3.0	124.4	25.0	1.0	24.5	145.0	3.0	144.7
K150-13-10	良	22.5	1.0	22.8	15.0	0.5	14.6	125.0	3.0	125.0	41.5	2.0	41.5	140.0	3.0	139.6
K150-13-13	良	30.0	1.0	30.6	20.0	1.0	20.5	125.0	3.0	124.0	23.0	1.0	23.2	145.0	3.0	144.5