

成形材料試験成績表

平成30年10月度



株式会社 未来樹



〒187-0043 東京都小平市学園東町1丁目7番14号
TEL:042-346-1100 FAX:042-346-2020

成形材料名:ポリエチレン

試験項目	試験方法	単位	規格値	試験値
密度	JIS K 7112	kg/m ³	942 以上	960
メルトフローレート	JIS K 7210	g/10min	1.5 以上 6.0 未満	5.3
引張降伏強さ	JIS K 7161	MPa	19.61 以上	27.86
デュロメータD硬さ	JIS K 7215	H _D D	60 以上	64
ビカッ軟化点	JIS K 7206	°C	105 以上	127

[備考] 本表は、材料メーカーの報告によるもので、当社製品の成形材料です。

K形スピーサ 試験成績書

平成 30年 10月度




株式会社 未来樹



〒187-0043 東京都小平市学園東町1丁目7番14号

TEL:042-346-1100 FAX:042-346-2020



項目 種類	外 観 形 状	K1			K2			K3			K4			全長		
		寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
旧K30-3-3	良	20.0	1.0	19.2	11.0	0.5	11.1	18.0	0.5	17.8	20.0	1.0	20.5	29.0	1.0	28.9
K30-3-3	良	30.0	1.0	29.7	11.0	0.5	11.0	18.0	0.5	17.8	20.0	1.0	20.8	29.0	1.0	28.8
旧K35-3-3	良	20.0	1.0	19.3	11.0	0.5	11.1	22.0	1.0	21.7	20.0	1.0	20.5	33.0	1.0	32.8
K35-3-3	良	30.0	1.0	29.7	11.0	0.5	11.1	22.0	1.0	21.7	20.0	1.0	20.6	33.0	1.0	32.8
旧K40-3-3	良	20.0	1.0	19.9	11.0	0.5	11.1	27.0	1.0	27.1	20.0	1.0	20.4	38.0	1.0	38.2
K40-3-3	良	30.0	1.0	30.1	11.0	0.5	11.3	27.0	1.0	27.0	20.0	1.0	20.6	38.0	1.0	38.3
K40-5-4	良	30.0	1.0	30.0	15.0	0.5	15.0	23.0	1.0	23.0	19.0	0.5	18.9	38.0	1.0	38.0
旧K45-3-3	良	20.0	1.0	20.0	11.0	0.5	11.4	32.0	1.0	32.1	20.0	1.0	20.6	43.0	2.0	43.5
K45-3-3	良	30.0	1.0	29.9	11.0	0.5	10.9	32.0	1.0	32.2	20.0	1.0	20.6	43.0	2.0	43.1
K45-5-4	良	30.0	1.0	30.2	15.0	0.5	15.1	28.0	1.0	28.1	19.0	0.5	19.2	43.0	2.0	43.2
K45-6-4	良	30.0	1.0	29.8	15.0	0.5	15.3	29.0	1.0	29.0	20.0	1.0	20.1	44.0	2.0	44.3
旧K50-4-4	良	20.0	1.0	20.1	15.0	0.5	15.4	33.0	1.0	32.3	20.0	1.0	20.1	48.0	2.0	47.7
K50-4-4	良	30.0	1.0	29.7	15.0	0.5	15.5	33.0	1.0	32.4	20.0	1.0	20.3	48.0	2.0	47.9
K50-5-4	良	30.0	1.0	29.9	15.0	0.5	15.1	33.0	1.0	33.0	19.0	0.5	19.2	48.0	2.0	48.1
K50-6-4	良	30.0	1.0	29.9	15.0	0.5	15.2	33.0	1.0	33.3	20.0	1.0	20.1	48.0	2.0	48.5
K50-6-6S	良	16.0	0.5	15.6	12.0	0.5	11.7	35.0	1.0	35.8	17.0	0.5	16.7	47.0	2.0	47.5
旧K55-5-4	良	20.0	1.0	19.2	15.0	0.5	14.7	37.0	1.0	36.7	20.0	1.0	20.4	52.0	2.0	51.4
K55-5-4	良	30.0	1.0	29.9	15.0	0.5	15.1	37.0	1.0	37.1	20.0	1.0	20.8	52.0	2.0	52.2
K55-6-4	良	30.0	1.0	29.8	15.0	0.5	14.9	38.0	1.0	38.3	20.0	1.0	20.1	53.0	2.0	53.2
K60-6-4	良	30.0	1.0	29.9	15.0	0.5	15.4	43.0	2.0	43.2	20.0	1.0	20.1	58.0	2.0	58.6
K60-6-6JR	良	30.0	1.0	29.9	17.0	0.5	17.0	41.0	2.0	40.5	29.0	1.0	28.4	58.0	2.0	57.5
K60-6-6S	良	17.0	0.5	17.1	11.0	0.5	11.3	45.0	2.0	43.8	17.0	0.5	16.7	56.0	2.0	55.1
K65-6-4	良	30.0	1.0	29.7	15.0	0.5	15.2	48.0	2.0	48.4	20.0	1.0	20.2	63.0	2.5	63.6
K70-6-6	良	30.0	1.0	29.7	15.0	0.5	14.8	53.0	2.0	54.0	20.0	1.0	19.9	68.0	2.5	68.8
K70-6-6P	良	25.0	1.0	24.7	16.0	0.5	16.2	51.0	2.0	50.9	27.0	1.0	26.5	67.0	2.5	67.1
K70-10-10	良	18.0	0.5	18.2	9.0	0.5	9.2	58.0	2.0	57.7	22.0	1.0	22.2	67.0	2.5	66.9
K74-6-6L	良	30.0	1.0	31.0	6.0	0.5	6.3	59.0	2.0	59.4	20.0	1.0	19.7	65.0	2.5	65.7
K80-4-4L	良	30.0	1.0	30.1	6.0	0.5	6.5	57.0	2.0	56.5	22.0	1.0	21.8	63.0	2.5	63.0
K80-6-6	良	30.0	1.0	29.0	15.0	0.5	15.1	63.0	2.5	64.0	20.0	1.0	20.0	78.0	2.5	79.1
K80-6-6L	良	30.0	1.0	30.9	6.0	0.5	6.3	65.0	2.5	66.0	20.0	1.0	19.5	71.0	2.5	72.3
旧K80-10-6	良	20.0	1.0	20.3	8.0	0.5	8.4	69.0	2.5	68.8	10.0	0.5	9.5	77.0	2.5	77.2

種類	項目 外觀形状	K1			K2			K3			K4			全長		
		寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
K80-10-6	良	30.0	1.0	30.8	16.0	0.5	15.6	62.0	2.5	62.7	30.0	1.0	30.2	78.0	2.5	78.3
K80-10-10	良	18.0	0.5	18.2	9.0	0.5	9.2	68.0	2.5	67.6	22.0	1.0	22.1	77.0	2.5	76.8
K85-4-4L	良	30.0	1.0	30.0	6.0	0.5	6.5	64.0	2.5	64.0	22.0	1.0	22.0	70.0	2.5	70.5
旧K85-10-6	良	20.0	1.0	20.2	10.0	0.5	10.2	73.0	2.5	72.3	10.0	0.5	9.5	83.0	2.5	82.5
K85-10-6	良	30.0	1.0	29.9	16.0	0.5	16.2	67.0	2.5	67.8	30.0	1.0	30.1	83.0	2.5	84.0
K90-4-4L	良	30.0	1.0	30.1	6.0	0.5	6.4	69.0	2.5	69.2	22.0	1.0	21.9	75.0	2.5	75.6
K90-4-4S	良	30.0	1.0	29.7	33.0	1.0	32.6	55.0	2.0	55.0	27.0	1.0	26.6	88.0	2.5	87.6
K90-6-4	良	30.0	1.0	30.0	15.0	0.5	14.8	70.0	2.5	70.2	23.0	1.0	23.4	85.0	2.5	85.0
K90-10-6H	良	30.0	1.0	30.6	16.0	0.5	15.7	69.0	2.5	69.9	30.0	1.0	30.2	85.0	2.5	85.6
K90-10-6	良	20.0	1.0	19.4	15.0	0.5	15.3	70.0	2.5	71.0	23.0	1.0	23.5	85.0	2.5	86.3
K90-10-6L	良	30.0	1.0	29.2	15.0	0.5	15.5	70.0	2.5	70.6	23.0	1.0	23.3	85.0	2.5	86.1
K95-4-4S	良	30.0	1.0	29.5	33.0	1.0	32.6	60.0	2.5	60.6	27.0	1.0	26.9	93.0	3.0	93.2
K95-6-6L	良	30.0	1.0	30.8	6.0	0.5	6.3	75.0	2.5	75.7	20.0	1.0	19.8	81.0	2.5	82.0
K95-6-6S	良	30.0	1.0	29.7	17.0	0.5	16.7	76.0	2.5	75.6	29.0	1.0	28.2	93.0	3.0	92.3
K95-10-6	良	30.0	1.0	29.7	20.0	1.0	19.7	70.0	2.5	70.5	23.0	1.0	22.5	90.0	3.0	90.2
K95-10-6H	良	30.0	1.0	30.4	16.0	0.5	15.8	74.0	2.5	76.0	30.0	1.0	30.3	90.0	3.0	91.8
K95-10-10	良	30.0	1.0	29.9	20.0	1.0	20.3	70.0	2.5	69.8	25.0	1.0	24.7	90.0	3.0	90.1
K95-13-6	良	22.0	1.0	21.9	20.0	1.0	20.4	70.0	2.5	70.7	23.0	1.0	23.4	90.0	3.0	91.1
K95-13-6L	良	30.0	1.0	30.2	20.0	1.0	19.5	70.0	2.5	71.0	23.0	1.0	23.1	90.0	3.0	90.5
K95-13-13	良	30.0	1.0	30.7	18.0	0.5	18.5	72.0	2.5	71.0	23.0	1.0	22.9	90.0	3.0	89.5
K100-10-6H	良	30.0	1.0	30.9	16.0	0.5	15.6	79.0	2.5	79.0	30.0	1.0	30.3	95.0	3.0	94.6
K100-10-6P	良	25.0	1.0	24.6	15.0	0.5	15.5	81.0	2.5	80.0	25.0	1.0	24.3	96.0	3.0	95.5
K100-10-10	良	30.0	1.0	29.9	19.0	0.5	18.5	76.0	2.5	76.1	24.0	1.0	23.5	95.0	3.0	94.6
K100-13-10	良	22.5	1.0	22.8	15.0	0.5	14.5	75.0	2.5	76.5	41.5	2.0	41.4	90.0	3.0	91.0
K100-13-13	良	22.0	1.0	21.8	15.0	0.5	15.5	80.0	2.5	79.3	23.0	1.0	22.2	95.0	3.0	94.8
K105-6-6H	良	25.0	1.0	24.5	17.0	0.5	16.6	83.0	2.5	82.8	26.0	1.0	26.3	100.0	3.0	99.4
K110-4-4S	良	30.0	1.0	29.8	43.0	2.0	42.6	65.0	2.5	64.9	27.0	1.0	26.8	108.0	3.0	107.5
K110-6-6H	良	25.0	1.0	24.7	17.0	0.5	16.6	88.0	2.5	88.3	27.0	1.0	26.3	105.0	3.0	104.9
K110-10-6	良	30.0	1.0	29.8	20.0	1.0	19.8	85.0	2.5	85.3	23.0	1.0	22.9	105.0	3.0	105.1
K110-10-6H	良	30.0	1.0	30.9	16.0	0.5	15.6	89.0	2.5	89.4	30.0	1.0	29.9	105.0	3.0	105.0
K110-10-10	良	30.0	1.0	30.4	20.0	1.0	20.5	82.0	2.5	81.9	24.0	1.0	24.2	102.0	3.0	102.4
K110-13-6	良	22.0	1.0	21.8	20.0	1.0	19.9	85.0	2.5	84.5	23.0	1.0	23.1	105.0	3.0	104.4
K110-13-6L	良	30.0	1.0	29.9	20.0	1.0	19.6	85.0	2.5	84.0	23.0	1.0	23.0	105.0	3.0	103.6
K110-13-13	良	30.0	1.0	30.6	20.0	1.0	20.2	84.0	2.5	84.0	23.0	1.0	23.0	104.0	3.0	104.2
K115-6-6H	良	25.0	1.0	24.6	17.0	0.5	16.5	93.0	3.0	92.7	27.0	1.0	26.4	110.0	3.0	109.2
K120-6-6H	良	25.0	1.0	24.5	17.0	0.5	16.6	98.0	3.0	98.0	27.0	1.0	26.3	115.0	3.0	114.6
K120-10-6H	良	30.0	1.0	30.6	16.0	0.5	15.7	99.0	3.0	99.0	30.0	1.0	30.0	115.0	3.0	114.7
K120-10-10	良	30.0	1.0	30.4	20.0	1.0	20.3	95.0	3.0	94.6	24.0	1.0	24.2	115.0	3.0	114.9
K120-13-10	良	22.5	1.0	22.3	15.0	0.5	15.0	95.0	3.0	95.8	41.5	2.0	41.7	110.0	3.0	110.8
K120-13-13	良	30.0	1.0	30.4	20.0	1.0	19.8	95.0	3.0	95.1	23.0	1.0	23.2	115.0	3.0	114.9
K125-4-4S	良	30.0	1.0	29.5	48.0	2.0	47.2	75.0	2.5	75.1	27.0	1.0	26.6	123.0	3.0	122.3
K125-10-6	良	30.0	1.0	29.8	20.0	1.0	19.5	100.0	3.0	100.0	23.0	1.0	22.6	120.0	3.0	119.5
K125-13-6	良	22.0	1.0	21.7	20.0	1.0	20.0	100.0	3.0	99.9	23.0	1.0	23.4	120.0	3.0	119.9
K125-13-6L	良	30.0	1.0	30.1	20.0	1.0	20.5	100.0	3.0	99.1	23.0	1.0	23.2	120.0	3.0	119.6
K130-10-10	良	30.0	1.0	30.8	20.0	1.0	20.3	105.0	3.0	105.9	25.0	1.0	24.4	125.0	3.0	126.2
K130-13-10	良	22.5	1.0	22.4	15.0	0.5	14.9	105.0	3.0	106.6	41.5	2.0	41.6	120.0	3.0	121.5
K130-13-13	良	30.0	1.0	30.4	20.0	1.0	20.2	105.0	3.0	105.2	23.0	1.0	23.5	125.0	3.0	125.4
K135-10-6H	良	30.0	1.0	30.1	16.0	0.5	15.9	114.0	3.0	114.1	30.0	1.0	29.8	130.0	3.0	130.0
K145-10-6H	良	30.0	1.0	30.3	16.0	0.5	15.6	124.0	3.0	123.6	30.0	1.0	29.6	140.0	3.0	139.2
K150-10-10	良	30.0	1.0	30.0	20.0	1.0	19.8	125.0	3.0	124.0	25.0	1.0	24.6	145.0	3.0	143.8
K150-13-10	良	22.5	1.0	22.8	15.0	0.5	14.9	125.0	3.0	126.1	41.5	2.0	41.4	140.0	3.0	141.0
K150-13-13	良	30.0	1.0	30.2	20.0	1.0	19.7	125.0	3.0	124.9	23.0	1.0	23.1	145.0	3.0	144.6