

成形材料試験成績表

平成31年2月度



株式会社 未来樹脂



〒187-0043 東京都小平市学園東町1丁目7番14号
TEL:042-346-1100 FAX:042-346-2020

成形材料名: ポリエチレン

試験項目	試験方法	単位	規格値	試験値
密度	JIS K 7112	kg/m ³	942 以上	962
メルトフローレート	JIS K 7210	g/10min	1.5 以上 6.0 未満	5.2
引張降伏強さ	JIS K 7161	MPa	19.61 以上	27.89
デュロメータD硬さ	JIS K 7215	H _D D	60 以上	64
ビカッ軟化点	JIS K 7206	°C	105 以上	127

[備考] 本表は、材料メーカーの報告によるもので、当社製品の成形材料です。

K形スピーサ 試験成績書

平成 31年 2月度







株式会社 未来樹



〒187-0043 東京都小平市学園東町1丁目7番14号

TEL:042-346-1100 FAX:042-346-2020



項目 種類	外 観 形 状	K1			K2			K3			K4			全長		
		寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
旧K30-3-3	良	20.0	1.0	19.2	11.0	0.5	11.0	18.0	0.5	17.7	20.0	1.0	20.7	29.0	1.0	28.7
K30-3-3	良	30.0	1.0	30.0	11.0	0.5	11.2	18.0	0.5	17.8	20.0	1.0	20.8	29.0	1.0	29.0
旧K35-3-3	良	20.0	1.0	19.2	11.0	0.5	11.2	22.0	1.0	21.6	20.0	1.0	20.6	33.0	1.0	32.8
K35-3-3	良	30.0	1.0	29.7	11.0	0.5	11.0	22.0	1.0	22.0	20.0	1.0	20.9	33.0	1.0	33.0
旧K40-3-3	良	20.0	1.0	19.9	11.0	0.5	10.9	27.0	1.0	27.0	20.0	1.0	20.6	38.0	1.0	37.9
K40-3-3	良	30.0	1.0	30.0	11.0	0.5	11.1	27.0	1.0	27.1	20.0	1.0	20.7	38.0	1.0	38.2
K40-5-4	良	30.0	1.0	29.5	15.0	0.5	15.1	23.0	1.0	22.9	19.0	0.5	19.0	38.0	1.0	38.0
旧K45-3-3	良	20.0	1.0	20.0	11.0	0.5	11.3	32.0	1.0	32.3	20.0	1.0	20.6	43.0	2.0	43.6
K45-3-3	良	30.0	1.0	30.1	11.0	0.5	11.3	32.0	1.0	32.3	20.0	1.0	20.7	43.0	2.0	43.6
K45-5-4	良	30.0	1.0	29.8	15.0	0.5	15.3	28.0	1.0	28.2	19.0	0.5	18.9	43.0	2.0	43.5
K45-6-4	良	30.0	1.0	30.0	15.0	0.5	15.4	29.0	1.0	29.3	20.0	1.0	20.1	44.0	2.0	44.7
旧K50-4-4	良	20.0	1.0	20.1	15.0	0.5	15.4	33.0	1.0	32.3	20.0	1.0	20.4	48.0	2.0	47.7
K50-4-4	良	30.0	1.0	29.9	15.0	0.5	15.4	33.0	1.0	32.5	20.0	1.0	20.4	48.0	2.0	47.9
K50-5-4	良	30.0	1.0	30.2	15.0	0.5	15.0	33.0	1.0	32.9	19.0	0.5	19.3	48.0	2.0	47.9
K50-6-4	良	30.0	1.0	30.0	15.0	0.5	15.3	33.0	1.0	33.1	20.0	1.0	20.1	48.0	2.0	48.4
K50-6-6S	良	16.0	0.5	15.6	12.0	0.5	11.7	35.0	1.0	35.9	17.0	0.5	16.6	47.0	2.0	47.6
旧K55-5-4	良	20.0	1.0	19.1	15.0	0.5	15.1	37.0	1.0	36.6	20.0	1.0	20.6	52.0	2.0	51.7
K55-5-4	良	30.0	1.0	29.9	15.0	0.5	15.1	37.0	1.0	36.6	20.0	1.0	20.8	52.0	2.0	51.7
K55-6-4	良	30.0	1.0	29.8	15.0	0.5	14.9	38.0	1.0	38.1	20.0	1.0	20.1	53.0	2.0	53.0
K60-6-4	良	30.0	1.0	29.9	15.0	0.5	15.3	43.0	2.0	43.4	20.0	1.0	20.3	58.0	2.0	58.7
K60-6-6JR	良	30.0	1.0	29.5	17.0	0.5	16.9	41.0	2.0	40.6	29.0	1.0	28.5	58.0	2.0	57.5
K60-6-6S	良	17.0	0.5	17.3	11.0	0.5	11.3	45.0	2.0	43.7	17.0	0.5	16.5	56.0	2.0	55.0
K65-6-4	良	30.0	1.0	29.8	15.0	0.5	15.2	48.0	2.0	48.3	20.0	1.0	20.2	63.0	2.5	63.5
K70-6-6	良	30.0	1.0	29.7	15.0	0.5	14.6	53.0	2.0	53.1	20.0	1.0	19.7	68.0	2.5	67.7
K70-6-6P	良	25.0	1.0	24.5	16.0	0.5	16.4	51.0	2.0	50.9	27.0	1.0	26.7	67.0	2.5	67.3
K70-10-10	良	18.0	0.5	17.9	9.0	0.5	9.4	58.0	2.0	57.7	22.0	1.0	22.2	67.0	2.5	67.1
K74-6-6L	良	30.0	1.0	30.7	6.0	0.5	6.3	59.0	2.0	59.9	20.0	1.0	19.6	65.0	2.5	66.2
K80-4-4L	良	30.0	1.0	30.2	6.0	0.5	6.5	57.0	2.0	56.8	22.0	1.0	21.6	63.0	2.5	63.3
K80-6-6	良	30.0	1.0	29.1	15.0	0.5	14.8	63.0	2.5	64.0	20.0	1.0	19.7	78.0	2.5	78.8
K80-6-6L	良	30.0	1.0	30.8	6.0	0.5	6.4	65.0	2.5	65.9	20.0	1.0	19.5	71.0	2.5	72.3
旧K80-10-6	良	20.0	1.0	20.4	8.0	0.5	8.4	69.0	2.5	68.6	10.0	0.5	9.5	77.0	2.5	77.0

項目 種類	外觀 形状	K1			K2			K3			K4			全長		
		寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
K80-10-6	良	30.0	1.0	30.7	16.0	0.5	15.7	62.0	2.5	62.6	30.0	1.0	30.2	78.0	2.5	78.3
K80-10-10	良	18.0	0.5	17.9	9.0	0.5	9.2	68.0	2.5	67.5	22.0	1.0	22.1	77.0	2.5	76.7
K85-4-4L	良	30.0	1.0	30.1	6.0	0.5	6.5	64.0	2.5	63.5	22.0	1.0	22.0	70.0	2.5	70.0
旧K85-10-6	良	20.0	1.0	20.1	10.0	0.5	10.3	73.0	2.5	72.4	10.0	0.5	9.5	83.0	2.5	82.7
K85-10-6	良	30.0	1.0	29.8	16.0	0.5	15.9	67.0	2.5	67.7	30.0	1.0	30.3	83.0	2.5	83.6
K90-4-4L	良	30.0	1.0	29.9	6.0	0.5	6.4	69.0	2.5	69.0	22.0	1.0	21.9	75.0	2.5	75.4
K90-4-4S	良	30.0	1.0	29.8	33.0	1.0	32.4	55.0	2.0	55.4	27.0	1.0	26.9	88.0	2.5	87.8
K90-6-4	良	30.0	1.0	29.8	15.0	0.5	14.7	70.0	2.5	70.3	23.0	1.0	22.8	85.0	2.5	85.0
K90-10-6H	良	30.0	1.0	30.9	16.0	0.5	15.5	69.0	2.5	69.5	30.0	1.0	29.9	85.0	2.5	85.0
K90-10-6	良	20.0	1.0	19.2	15.0	0.5	15.4	70.0	2.5	70.9	23.0	1.0	23.5	85.0	2.5	86.3
K90-10-6L	良	30.0	1.0	29.3	15.0	0.5	15.4	70.0	2.5	70.8	23.0	1.0	23.6	85.0	2.5	86.2
K95-4-4S	良	30.0	1.0	29.4	33.0	1.0	32.4	60.0	2.5	60.8	27.0	1.0	26.7	93.0	3.0	93.2
K95-6-6L	良	30.0	1.0	30.9	6.0	0.5	6.4	75.0	2.5	75.6	20.0	1.0	19.8	81.0	2.5	82.0
K95-6-6S	良	30.0	1.0	30.1	17.0	0.5	16.9	76.0	2.5	75.8	29.0	1.0	28.5	93.0	3.0	92.7
K95-10-6	良	30.0	1.0	29.7	20.0	1.0	19.7	70.0	2.5	70.8	23.0	1.0	22.3	90.0	3.0	90.5
K95-10-6H	良	30.0	1.0	31.0	16.0	0.5	15.7	74.0	2.5	75.1	30.0	1.0	30.2	90.0	3.0	90.8
K95-10-10	良	30.0	1.0	30.5	20.0	1.0	19.6	70.0	2.5	69.9	25.0	1.0	24.3	90.0	3.0	89.5
K95-13-6	良	22.0	1.0	22.1	20.0	1.0	20.4	70.0	2.5	70.5	23.0	1.0	23.5	90.0	3.0	90.9
K95-13-6L	良	30.0	1.0	29.8	20.0	1.0	19.5	70.0	2.5	70.5	23.0	1.0	23.1	90.0	3.0	90.0
K95-13-13	良	30.0	1.0	30.6	18.0	0.5	18.5	72.0	2.5	71.5	23.0	1.0	23.1	90.0	3.0	90.0
K100-10-6H	良	30.0	1.0	30.7	16.0	0.5	15.7	79.0	2.5	79.5	30.0	1.0	30.0	95.0	3.0	95.2
K100-10-6P	良	25.0	1.0	24.9	15.0	0.5	15.5	81.0	2.5	80.6	25.0	1.0	24.4	96.0	3.0	96.1
K100-10-10	良	30.0	1.0	30.0	19.0	0.5	18.5	76.0	2.5	76.6	24.0	1.0	23.4	95.0	3.0	95.1
K100-13-10	良	22.5	1.0	22.7	15.0	0.5	14.9	75.0	2.5	76.7	41.5	2.0	41.6	90.0	3.0	91.6
K100-13-13	良	22.0	1.0	21.5	15.0	0.5	15.5	80.0	2.5	79.5	23.0	1.0	22.4	95.0	3.0	95.0
K105-6-6H	良	25.0	1.0	24.7	17.0	0.5	16.6	83.0	2.5	82.6	26.0	1.0	26.3	100.0	3.0	99.2
K110-4-4S	良	30.0	1.0	29.9	43.0	2.0	42.6	65.0	2.5	64.1	27.0	1.0	26.7	108.0	3.0	106.7
K110-6-6H	良	25.0	1.0	24.6	17.0	0.5	16.5	88.0	2.5	87.8	27.0	1.0	26.4	105.0	3.0	104.3
K110-10-6	良	30.0	1.0	29.6	20.0	1.0	20.2	85.0	2.5	85.2	23.0	1.0	22.4	105.0	3.0	105.4
K110-10-6H	良	30.0	1.0	30.6	16.0	0.5	15.7	89.0	2.5	89.1	30.0	1.0	30.1	105.0	3.0	104.8
K110-10-10	良	30.0	1.0	30.5	20.0	1.0	20.1	82.0	2.5	81.3	24.0	1.0	24.2	102.0	3.0	101.4
K110-13-6	良	22.0	1.0	21.7	20.0	1.0	19.5	85.0	2.5	84.8	23.0	1.0	23.3	105.0	3.0	104.3
K110-13-6L	良	30.0	1.0	30.0	20.0	1.0	19.6	85.0	2.5	84.8	23.0	1.0	23.0	105.0	3.0	104.4
K110-13-13	良	30.0	1.0	30.4	20.0	1.0	20.2	84.0	2.5	83.7	23.0	1.0	23.3	104.0	3.0	103.9
K115-6-6H	良	25.0	1.0	24.5	17.0	0.5	16.5	93.0	3.0	92.9	27.0	1.0	26.2	110.0	3.0	109.4
K120-6-6H	良	25.0	1.0	24.7	17.0	0.5	16.5	98.0	3.0	97.9	27.0	1.0	26.4	115.0	3.0	114.4
K120-10-6H	良	30.0	1.0	30.7	16.0	0.5	15.7	99.0	3.0	99.5	30.0	1.0	30.0	115.0	3.0	115.2
K120-10-10	良	30.0	1.0	30.3	20.0	1.0	19.9	95.0	3.0	94.8	24.0	1.0	24.0	115.0	3.0	114.7
K120-13-10	良	22.5	1.0	23.0	15.0	0.5	14.8	95.0	3.0	96.1	41.5	2.0	41.5	110.0	3.0	110.9
K120-13-13	良	30.0	1.0	30.2	20.0	1.0	20.0	95.0	3.0	95.9	23.0	1.0	23.3	115.0	3.0	115.9
K125-4-4S	良	30.0	1.0	29.6	48.0	2.0	47.2	75.0	2.5	74.3	27.0	1.0	26.6	123.0	3.0	121.5
K125-10-6	良	30.0	1.0	29.7	20.0	1.0	20.2	100.0	3.0	99.1	23.0	1.0	22.4	120.0	3.0	119.3
K125-13-6	良	22.0	1.0	22.0	20.0	1.0	19.6	100.0	3.0	98.8	23.0	1.0	23.1	120.0	3.0	118.4
K125-13-6L	良	30.0	1.0	29.8	20.0	1.0	19.8	100.0	3.0	98.9	23.0	1.0	23.3	120.0	3.0	118.7
K130-10-10	良	30.0	1.0	30.1	20.0	1.0	20.3	105.0	3.0	105.6	25.0	1.0	24.4	125.0	3.0	125.9
K130-13-10	良	22.5	1.0	22.3	15.0	0.5	14.8	105.0	3.0	105.6	41.5	2.0	41.5	120.0	3.0	120.4
K130-13-13	良	30.0	1.0	30.2	20.0	1.0	20.0	105.0	3.0	105.3	23.0	1.0	23.2	125.0	3.0	125.3
K135-10-6H	良	30.0	1.0	29.6	16.0	0.5	15.5	114.0	3.0	113.9	30.0	1.0	29.8	130.0	3.0	129.4
K145-10-6H	良	30.0	1.0	29.5	16.0	0.5	15.8	124.0	3.0	124.4	30.0	1.0	29.6	140.0	3.0	140.2
K150-10-10	良	30.0	1.0	30.8	20.0	1.0	19.8	125.0	3.0	124.3	25.0	1.0	24.4	145.0	3.0	144.1
K150-13-10	良	22.5	1.0	22.4	15.0	0.5	14.6	125.0	3.0	125.9	41.5	2.0	41.5	140.0	3.0	140.5
K150-13-13	良	30.0	1.0	30.7	20.0	1.0	20.1	125.0	3.0	124.7	23.0	1.0	23.3	145.0	3.0	144.8