


成形材料試験成績表

令和2年5月度



〒181-0013 東京都三鷹市下連雀3-38-4
三鷹産業プラザ5F
TEL:0422-70-4201 FAX:0422-43-1021

成形材料名:ポリエチレン

試験項目	試験方法	単位	規格値	試験値
密度	JIS K 7112	kg/m ³	942 以上	963
メルトフローレート	JIS K 7210	g/10min	1.5 以上 6.0 未満	5.0
引張降伏強さ	JIS K 7161	MPa	19.61 以上	28.05
デュロメータD硬さ	JIS K 7215	H _D D	60 以上	63
ビカッ軟化点	JIS K 7206	°C	105 以上	127

[備考] 本表は、材料メーカーの報告によるもので、当社製品の成形材料です。

K形スピーサ 試験成績書





令和 2年 5月度



株式会社 未来樹

〒181-0013 東京都三鷹市下連雀 3-38-4
三鷹産業プラザ5F

TEL:0422-70-4201 FAX:0422-43-1021



項目 種類	外 観 形 状	K1			K2			K3			K4			全長		
		寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
旧K30-3-3	良	20.0	1.0	19.4	11.0	0.5	10.8	18.0	0.5	17.7	20.0	1.0	20.8	29.0	1.0	28.5
K30-3-3	良	30.0	1.0	29.7	11.0	0.5	11.2	18.0	0.5	17.9	20.0	1.0	20.9	29.0	1.0	29.1
旧K35-3-3	良	20.0	1.0	19.4	11.0	0.5	11.1	22.0	1.0	21.6	20.0	1.0	20.8	33.0	1.0	32.7
K35-3-3	良	30.0	1.0	29.9	11.0	0.5	11.3	22.0	1.0	21.8	20.0	1.0	20.8	33.0	1.0	33.1
旧K40-3-3	良	20.0	1.0	20.0	11.0	0.5	11.1	27.0	1.0	27.0	20.0	1.0	20.6	38.0	1.0	38.1
K40-3-3	良	30.0	1.0	30.0	11.0	0.5	11.2	27.0	1.0	27.2	20.0	1.0	20.6	38.0	1.0	38.4
K40-5-4	良	30.0	1.0	30.0	15.0	0.5	15.1	23.0	1.0	22.9	19.0	0.5	18.8	38.0	1.0	38.0
旧K45-3-3	良	20.0	1.0	20.0	11.0	0.5	11.3	32.0	1.0	32.2	20.0	1.0	20.4	43.0	2.0	43.5
K45-3-3	良	30.0	1.0	30.1	11.0	0.5	11.1	32.0	1.0	32.3	20.0	1.0	20.6	43.0	2.0	43.4
K45-5-4	良	30.0	1.0	29.9	15.0	0.5	15.2	28.0	1.0	28.0	19.0	0.5	19.3	43.0	2.0	43.2
K45-6-4	良	30.0	1.0	30.0	15.0	0.5	15.1	29.0	1.0	29.1	20.0	1.0	20.2	44.0	2.0	44.2
旧K50-4-4	良	20.0	1.0	20.0	15.0	0.5	15.5	33.0	1.0	32.2	20.0	1.0	20.2	48.0	2.0	47.7
K50-4-4	良	30.0	1.0	29.9	15.0	0.5	15.4	33.0	1.0	32.4	20.0	1.0	20.3	48.0	2.0	47.8
K50-5-4	良	30.0	1.0	29.7	15.0	0.5	15.2	33.0	1.0	32.5	19.0	0.5	18.8	48.0	2.0	47.7
K50-6-4	良	30.0	1.0	30.1	15.0	0.5	15.0	33.0	1.0	33.4	20.0	1.0	20.2	48.0	2.0	48.4
K50-6-6S	良	16.0	0.5	15.6	12.0	0.5	11.9	35.0	1.0	35.9	17.0	0.5	16.7	47.0	2.0	47.8
旧K55-5-4	良	20.0	1.0	19.2	15.0	0.5	15.2	37.0	1.0	36.5	20.0	1.0	20.6	52.0	2.0	51.7
K55-5-4	良	30.0	1.0	29.8	15.0	0.5	15.1	37.0	1.0	37.2	20.0	1.0	20.4	52.0	2.0	52.3
K55-6-4	良	30.0	1.0	30.0	15.0	0.5	15.4	38.0	1.0	38.1	20.0	1.0	20.3	53.0	2.0	53.5
K60-6-4	良	30.0	1.0	30.1	15.0	0.5	15.1	43.0	2.0	43.2	20.0	1.0	20.2	58.0	2.0	58.3
K60-6-6JR	良	30.0	1.0	29.4	17.0	0.5	16.7	41.0	2.0	40.7	29.0	1.0	28.3	58.0	2.0	57.4
K60-6-6S	良	17.0	0.5	17.3	11.0	0.5	11.4	45.0	2.0	43.6	17.0	0.5	16.8	56.0	2.0	55.0
K65-6-4	良	30.0	1.0	29.8	15.0	0.5	15.4	48.0	2.0	48.0	20.0	1.0	20.1	63.0	2.5	63.4
K70-6-6	良	30.0	1.0	29.7	15.0	0.5	14.7	53.0	2.0	53.1	20.0	1.0	19.9	68.0	2.5	67.8
K70-6-6P	良	25.0	1.0	24.6	16.0	0.5	16.4	51.0	2.0	50.6	27.0	1.0	26.7	67.0	2.5	67.0
K70-10-10	良	18.0	0.5	17.9	9.0	0.5	9.2	58.0	2.0	57.7	22.0	1.0	21.9	67.0	2.5	66.9
K74-6-6L	良	30.0	1.0	30.8	6.0	0.5	6.5	59.0	2.0	59.5	20.0	1.0	19.7	65.0	2.5	66.0
K80-4-4L	良	30.0	1.0	29.9	6.0	0.5	6.4	57.0	2.0	57.1	22.0	1.0	21.8	63.0	2.5	63.5
K80-6-6	良	30.0	1.0	29.0	15.0	0.5	14.9	63.0	2.5	64.2	20.0	1.0	20.2	78.0	2.5	79.1
K80-6-6L	良	30.0	1.0	30.9	6.0	0.5	6.4	65.0	2.5	66.1	20.0	1.0	19.7	71.0	2.5	72.5
旧K80-10-6	良	20.0	1.0	20.1	8.0	0.5	8.4	69.0	2.5	68.5	10.0	0.5	9.5	77.0	2.5	76.9

項目 種類	外 観 形 状	K1			K2			K3			K4			全長		
		寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
K80-10-6	良	30.0	1.0	30.6	16.0	0.5	15.8	62.0	2.5	62.5	30.0	1.0	29.9	78.0	2.5	78.3
K80-10-10	良	18.0	0.5	17.9	9.0	0.5	9.2	68.0	2.5	67.7	22.0	1.0	22.0	77.0	2.5	76.9
K85-4-4L	良	30.0	1.0	30.1	6.0	0.5	6.4	64.0	2.5	63.5	22.0	1.0	21.9	70.0	2.5	69.9
旧K85-10-6	良	20.0	1.0	20.1	10.0	0.5	10.2	73.0	2.5	72.8	10.0	0.5	9.5	83.0	2.5	83.0
K85-10-6	良	30.0	1.0	29.8	16.0	0.5	16.0	67.0	2.5	67.8	30.0	1.0	30.0	83.0	2.5	83.8
K90-4-4L	良	30.0	1.0	30.0	6.0	0.5	6.5	69.0	2.5	69.5	22.0	1.0	21.8	75.0	2.5	76.0
K90-4-4S	良	30.0	1.0	29.8	33.0	1.0	32.9	55.0	2.0	55.4	27.0	1.0	26.9	88.0	2.5	88.3
K90-6-4	良	30.0	1.0	30.0	15.0	0.5	14.8	70.0	2.5	70.2	23.0	1.0	23.3	85.0	2.5	85.0
K90-10-6H	良	30.0	1.0	30.6	16.0	0.5	15.6	69.0	2.5	69.6	30.0	1.0	30.2	85.0	2.5	85.2
K90-10-6	良	20.0	1.0	19.3	15.0	0.5	15.4	70.0	2.5	70.8	23.0	1.0	23.5	85.0	2.5	86.2
K90-10-6L	良	30.0	1.0	29.4	15.0	0.5	15.4	70.0	2.5	71.0	23.0	1.0	23.3	85.0	2.5	86.4
K95-4-4S	良	30.0	1.0	29.8	33.0	1.0	32.7	60.0	2.5	60.6	27.0	1.0	27.0	93.0	3.0	93.3
K95-6-6L	良	30.0	1.0	30.8	6.0	0.5	6.4	75.0	2.5	75.8	20.0	1.0	19.8	81.0	2.5	82.2
K95-6-6S	良	30.0	1.0	29.7	17.0	0.5	17.0	76.0	2.5	75.4	29.0	1.0	28.3	93.0	3.0	92.4
K95-10-6	良	30.0	1.0	30.0	20.0	1.0	19.8	70.0	2.5	70.4	23.0	1.0	22.6	90.0	3.0	90.2
K95-10-6H	良	30.0	1.0	30.7	16.0	0.5	15.7	74.0	2.5	75.2	30.0	1.0	30.1	90.0	3.0	90.9
K95-10-10	良	30.0	1.0	30.4	20.0	1.0	20.4	70.0	2.5	69.6	25.0	1.0	24.4	90.0	3.0	90.0
K95-13-6	良	22.0	1.0	22.0	20.0	1.0	20.0	70.0	2.5	70.6	23.0	1.0	23.1	90.0	3.0	90.6
K95-13-6L	良	30.0	1.0	30.1	20.0	1.0	19.9	70.0	2.5	70.0	23.0	1.0	23.5	90.0	3.0	89.9
K95-13-13	良	30.0	1.0	30.5	18.0	0.5	18.5	72.0	2.5	71.6	23.0	1.0	23.1	90.0	3.0	90.1
K100-10-6H	良	30.0	1.0	30.7	16.0	0.5	15.7	79.0	2.5	79.4	30.0	1.0	30.1	95.0	3.0	95.1
K100-10-6P	良	25.0	1.0	24.8	15.0	0.5	15.5	81.0	2.5	80.3	25.0	1.0	24.9	96.0	3.0	95.8
K100-10-10	良	30.0	1.0	29.4	19.0	0.5	18.5	76.0	2.5	76.8	24.0	1.0	23.4	95.0	3.0	95.3
K100-13-10	良	22.5	1.0	22.8	15.0	0.5	14.6	75.0	2.5	76.4	41.5	2.0	41.6	90.0	3.0	91.0
K100-13-13	良	22.0	1.0	21.5	15.0	0.5	15.5	80.0	2.5	79.1	23.0	1.0	22.4	95.0	3.0	94.6
K105-6-6H	良	25.0	1.0	24.6	17.0	0.5	16.6	83.0	2.5	83.0	26.0	1.0	26.4	100.0	3.0	99.6
K110-4-4S	良	30.0	1.0	29.9	43.0	2.0	43.3	65.0	2.5	65.5	27.0	1.0	26.7	108.0	3.0	108.8
K110-6-6H	良	25.0	1.0	24.6	17.0	0.5	16.6	88.0	2.5	88.2	27.0	1.0	26.5	105.0	3.0	104.8
K110-10-6	良	30.0	1.0	29.8	20.0	1.0	19.2	85.0	2.5	85.1	23.0	1.0	22.8	105.0	3.0	104.3
K110-10-6H	良	30.0	1.0	30.7	16.0	0.5	15.7	89.0	2.5	88.9	30.0	1.0	30.0	105.0	3.0	104.6
K110-10-10	良	30.0	1.0	30.8	20.0	1.0	20.1	82.0	2.5	81.6	24.0	1.0	24.2	102.0	3.0	101.7
K110-13-6	良	22.0	1.0	21.9	20.0	1.0	20.1	85.0	2.5	84.4	23.0	1.0	23.0	105.0	3.0	104.5
K110-13-6L	良	30.0	1.0	29.8	20.0	1.0	20.4	85.0	2.5	84.6	23.0	1.0	23.0	105.0	3.0	105.0
K110-13-13	良	30.0	1.0	30.3	20.0	1.0	20.0	84.0	2.5	83.8	23.0	1.0	23.1	104.0	3.0	103.8
K115-6-6H	良	25.0	1.0	24.8	17.0	0.5	16.5	93.0	3.0	92.5	27.0	1.0	26.4	110.0	3.0	109.0
K120-6-6H	良	25.0	1.0	24.7	17.0	0.5	16.5	98.0	3.0	98.2	27.0	1.0	26.4	115.0	3.0	114.7
K120-10-6H	良	30.0	1.0	30.7	16.0	0.5	15.7	99.0	3.0	99.4	30.0	1.0	30.1	115.0	3.0	115.1
K120-10-10	良	30.0	1.0	30.4	20.0	1.0	19.8	95.0	3.0	94.5	24.0	1.0	24.2	115.0	3.0	114.3
K120-13-10	良	22.5	1.0	22.2	15.0	0.5	14.6	95.0	3.0	95.9	41.5	2.0	41.5	110.0	3.0	110.5
K120-13-13	良	30.0	1.0	30.3	20.0	1.0	19.7	95.0	3.0	95.3	23.0	1.0	23.4	115.0	3.0	115.0
K125-4-4S	良	30.0	1.0	29.7	48.0	2.0	47.3	75.0	2.5	74.6	27.0	1.0	26.9	123.0	3.0	121.9
K125-10-6	良	30.0	1.0	29.9	20.0	1.0	19.3	100.0	3.0	99.8	23.0	1.0	22.2	120.0	3.0	119.1
K125-13-6	良	22.0	1.0	21.7	20.0	1.0	19.5	100.0	3.0	99.0	23.0	1.0	23.1	120.0	3.0	118.5
K125-13-6L	良	30.0	1.0	30.0	20.0	1.0	20.5	100.0	3.0	98.7	23.0	1.0	23.0	120.0	3.0	119.2
K130-10-10	良	30.0	1.0	30.3	20.0	1.0	19.8	105.0	3.0	105.8	25.0	1.0	24.3	125.0	3.0	125.6
K130-13-10	良	22.5	1.0	22.6	15.0	0.5	15.0	105.0	3.0	105.4	41.5	2.0	41.5	120.0	3.0	120.4
K130-13-13	良	30.0	1.0	30.5	20.0	1.0	19.9	105.0	3.0	105.8	23.0	1.0	23.4	125.0	3.0	125.7
K135-10-6H	良	30.0	1.0	30.2	16.0	0.5	15.9	114.0	3.0	113.8	30.0	1.0	29.5	130.0	3.0	129.7
K145-10-6H	良	30.0	1.0	30.0	16.0	0.5	15.6	124.0	3.0	123.6	30.0	1.0	29.5	140.0	3.0	139.2
K150-10-10	良	30.0	1.0	30.5	20.0	1.0	20.3	125.0	3.0	124.7	25.0	1.0	24.6	145.0	3.0	145.0
K150-13-10	良	22.5	1.0	22.3	15.0	0.5	14.7	125.0	3.0	125.4	41.5	2.0	41.7	140.0	3.0	140.1
K150-13-13	良	30.0	1.0	30.4	20.0	1.0	20.2	125.0	3.0	123.6	23.0	1.0	23.1	145.0	3.0	143.8