

成形材料試験成績表

令和2年6月度



株式会社 未来樹



〒181-0013 東京都三鷹市下連雀3-38-4
三鷹産業プラザ5F

TEL:0422-70-4201 FAX:0422-43-1021

成形材料名: ポリエチレン

試験項目	試験方法	単位	規格値	試験値
密度	JIS K 7112	kg/m ³	942 以上	962
メルトフローレート	JIS K 7210	g/10min	1.5 以上 6.0 未満	5.3
引張降伏強さ	JIS K 7161	MPa	19.61 以上	27.92
デュロメータD硬さ	JIS K 7215	H _D D	60 以上	64
ビカッ軟化点	JIS K 7206	°C	105 以上	127

[備考] 本表は、材料メーカーの報告によるもので、当社製品の成形材料です。

K形スピーサ 試験成績書





令和 2年 6月度



株式会社 未来樹

〒181-0013 東京都三鷹市下連雀 3-38-4
三鷹産業プラザ5F

TEL:0422-70-4201 FAX:0422-43-1021



項目 種類	外 観 形 状	K1			K2			K3			K4			全長		
		寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値	寸法	許容差	測定値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
旧K30-3-3	良	20.0	1.0	19.3	11.0	0.5	11.1	18.0	0.5	17.8	20.0	1.0	20.5	29.0	1.0	28.9
K30-3-3	良	30.0	1.0	29.9	11.0	0.5	11.0	18.0	0.5	17.8	20.0	1.0	20.9	29.0	1.0	28.8
旧K35-3-3	良	20.0	1.0	19.3	11.0	0.5	10.9	22.0	1.0	21.6	20.0	1.0	20.8	33.0	1.0	32.5
K35-3-3	良	30.0	1.0	29.7	11.0	0.5	11.0	22.0	1.0	22.1	20.0	1.0	20.9	33.0	1.0	33.1
旧K40-3-3	良	20.0	1.0	20.0	11.0	0.5	11.1	27.0	1.0	26.9	20.0	1.0	20.5	38.0	1.0	38.0
K40-3-3	良	30.0	1.0	30.0	11.0	0.5	10.9	27.0	1.0	27.1	20.0	1.0	20.7	38.0	1.0	38.0
K40-5-4	良	30.0	1.0	30.0	15.0	0.5	15.2	23.0	1.0	22.9	19.0	0.5	18.9	38.0	1.0	38.1
旧K45-3-3	良	20.0	1.0	19.9	11.0	0.5	11.4	32.0	1.0	32.0	20.0	1.0	20.5	43.0	2.0	43.4
K45-3-3	良	30.0	1.0	30.1	11.0	0.5	11.0	32.0	1.0	32.3	20.0	1.0	20.7	43.0	2.0	43.3
K45-5-4	良	30.0	1.0	30.1	15.0	0.5	15.3	28.0	1.0	28.3	19.0	0.5	19.1	43.0	2.0	43.6
K45-6-4	良	30.0	1.0	29.9	15.0	0.5	15.3	29.0	1.0	29.4	20.0	1.0	20.0	44.0	2.0	44.7
旧K50-4-4	良	20.0	1.0	19.7	15.0	0.5	15.5	33.0	1.0	32.4	20.0	1.0	20.2	48.0	2.0	47.9
K50-4-4	良	30.0	1.0	29.9	15.0	0.5	15.4	33.0	1.0	32.5	20.0	1.0	20.4	48.0	2.0	47.9
K50-5-4	良	30.0	1.0	29.8	15.0	0.5	15.1	33.0	1.0	32.8	19.0	0.5	19.2	48.0	2.0	47.9
K50-6-4	良	30.0	1.0	30.0	15.0	0.5	15.2	33.0	1.0	33.2	20.0	1.0	20.1	48.0	2.0	48.4
K50-6-6S	良	16.0	0.5	15.5	12.0	0.5	11.8	35.0	1.0	35.9	17.0	0.5	16.7	47.0	2.0	47.7
旧K55-5-4	良	20.0	1.0	19.1	15.0	0.5	15.0	37.0	1.0	37.1	20.0	1.0	20.2	52.0	2.0	52.1
K55-5-4	良	30.0	1.0	29.8	15.0	0.5	14.8	37.0	1.0	37.6	20.0	1.0	20.6	52.0	2.0	52.4
K55-6-4	良	30.0	1.0	29.9	15.0	0.5	14.9	38.0	1.0	38.2	20.0	1.0	20.2	53.0	2.0	53.1
K60-6-4	良	30.0	1.0	30.1	15.0	0.5	15.1	43.0	2.0	43.3	20.0	1.0	20.3	58.0	2.0	58.4
K60-6-6JR	良	30.0	1.0	29.8	17.0	0.5	16.9	41.0	2.0	40.8	29.0	1.0	28.3	58.0	2.0	57.7
K60-6-6S	良	17.0	0.5	17.2	11.0	0.5	11.5	45.0	2.0	43.8	17.0	0.5	16.8	56.0	2.0	55.3
K65-6-4	良	30.0	1.0	29.9	15.0	0.5	15.2	48.0	2.0	48.1	20.0	1.0	20.2	63.0	2.5	63.3
K70-6-6	良	30.0	1.0	30.0	15.0	0.5	15.0	53.0	2.0	53.2	20.0	1.0	19.8	68.0	2.5	68.2
K70-6-6P	良	25.0	1.0	24.7	16.0	0.5	16.5	51.0	2.0	50.7	27.0	1.0	26.5	67.0	2.5	67.2
K70-10-10	良	18.0	0.5	17.8	9.0	0.5	9.2	58.0	2.0	57.8	22.0	1.0	21.9	67.0	2.5	67.0
K74-6-6L	良	30.0	1.0	30.9	6.0	0.5	6.4	59.0	2.0	59.5	20.0	1.0	19.5	65.0	2.5	65.9
K80-4-4L	良	30.0	1.0	30.2	6.0	0.5	6.4	57.0	2.0	57.0	22.0	1.0	21.6	63.0	2.5	63.4
K80-6-6	良	30.0	1.0	29.1	15.0	0.5	14.9	63.0	2.5	64.2	20.0	1.0	20.0	78.0	2.5	79.1
K80-6-6L	良	30.0	1.0	30.8	6.0	0.5	6.4	65.0	2.5	66.0	20.0	1.0	19.6	71.0	2.5	72.4
旧K80-10-6	良	20.0	1.0	20.1	8.0	0.5	8.5	69.0	2.5	68.5	10.0	0.5	9.5	77.0	2.5	77.0

項目 種類	外 観 形 状	K1			K2			K3			K4			全長		
		寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値	寸 法	許 容 差	測 定 値
		mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm	mm	±	mm
K80-10-6	良	30.0	1.0	30.9	16.0	0.5	15.5	62.0	2.5	62.4	30.0	1.0	30.1	78.0	2.5	77.9
K80-10-10	良	18.0	0.5	17.9	9.0	0.5	9.2	68.0	2.5	67.6	22.0	1.0	22.2	77.0	2.5	76.8
K85-4-4L	良	30.0	1.0	29.9	6.0	0.5	6.4	64.0	2.5	64.3	22.0	1.0	21.7	70.0	2.5	70.7
旧K85-10-6	良	20.0	1.0	20.2	10.0	0.5	10.3	73.0	2.5	72.6	10.0	0.5	9.5	83.0	2.5	82.9
K85-10-6	良	30.0	1.0	30.0	16.0	0.5	16.0	67.0	2.5	67.7	30.0	1.0	30.2	83.0	2.5	83.7
K90-4-4L	良	30.0	1.0	29.9	6.0	0.5	6.4	69.0	2.5	69.3	22.0	1.0	22.0	75.0	2.5	75.7
K90-4-4S	良	30.0	1.0	29.5	33.0	1.0	32.7	55.0	2.0	55.1	27.0	1.0	26.8	88.0	2.5	87.8
K90-6-4	良	30.0	1.0	29.7	15.0	0.5	14.6	70.0	2.5	70.7	23.0	1.0	23.0	85.0	2.5	85.3
K90-10-6H	良	30.0	1.0	30.9	16.0	0.5	15.7	69.0	2.5	69.5	30.0	1.0	30.2	85.0	2.5	85.2
K90-10-6	良	20.0	1.0	19.1	15.0	0.5	15.4	70.0	2.5	70.5	23.0	1.0	23.2	85.0	2.5	85.9
K90-10-6L	良	30.0	1.0	29.1	15.0	0.5	15.2	70.0	2.5	70.8	23.0	1.0	23.6	85.0	2.5	86.0
K95-4-4S	良	30.0	1.0	29.5	33.0	1.0	32.4	60.0	2.5	59.9	27.0	1.0	26.9	93.0	3.0	92.3
K95-6-6L	良	30.0	1.0	30.9	6.0	0.5	6.4	75.0	2.5	75.6	20.0	1.0	19.8	81.0	2.5	82.0
K95-6-6S	良	30.0	1.0	29.3	17.0	0.5	16.9	76.0	2.5	75.6	29.0	1.0	28.3	93.0	3.0	92.5
K95-10-6	良	30.0	1.0	29.6	20.0	1.0	20.2	70.0	2.5	70.8	23.0	1.0	22.9	90.0	3.0	91.0
K95-10-6H	良	30.0	1.0	30.4	16.0	0.5	15.7	74.0	2.5	75.9	30.0	1.0	29.9	90.0	3.0	91.6
K95-10-10	良	30.0	1.0	30.3	20.0	1.0	20.5	70.0	2.5	69.9	25.0	1.0	24.3	90.0	3.0	90.4
K95-13-6	良	22.0	1.0	21.7	20.0	1.0	19.6	70.0	2.5	71.1	23.0	1.0	23.1	90.0	3.0	90.7
K95-13-6L	良	30.0	1.0	29.7	20.0	1.0	20.1	70.0	2.5	70.7	23.0	1.0	23.0	90.0	3.0	90.8
K95-13-13	良	30.0	1.0	29.9	18.0	0.5	18.5	72.0	2.5	71.0	23.0	1.0	22.9	90.0	3.0	89.5
K100-10-6H	良	30.0	1.0	30.6	16.0	0.5	15.7	79.0	2.5	79.0	30.0	1.0	30.0	95.0	3.0	94.7
K100-10-6P	良	25.0	1.0	25.1	15.0	0.5	15.5	81.0	2.5	80.5	25.0	1.0	24.8	96.0	3.0	96.0
K100-10-10	良	30.0	1.0	30.0	19.0	0.5	18.5	76.0	2.5	76.9	24.0	1.0	23.5	95.0	3.0	95.4
K100-13-10	良	22.5	1.0	23.0	15.0	0.5	14.7	75.0	2.5	76.4	41.5	2.0	41.5	90.0	3.0	91.1
K100-13-13	良	22.0	1.0	21.5	15.0	0.5	15.5	80.0	2.5	79.6	23.0	1.0	22.4	95.0	3.0	95.1
K105-6-6H	良	25.0	1.0	24.8	17.0	0.5	16.6	83.0	2.5	83.3	26.0	1.0	26.2	100.0	3.0	99.9
K110-4-4S	良	30.0	1.0	30.0	43.0	2.0	42.7	65.0	2.5	64.7	27.0	1.0	26.7	108.0	3.0	107.4
K110-6-6H	良	25.0	1.0	24.8	17.0	0.5	16.5	88.0	2.5	87.7	27.0	1.0	26.4	105.0	3.0	104.2
K110-10-6	良	30.0	1.0	29.7	20.0	1.0	20.0	85.0	2.5	84.6	23.0	1.0	22.7	105.0	3.0	104.6
K110-10-6H	良	30.0	1.0	31.0	16.0	0.5	15.6	89.0	2.5	89.2	30.0	1.0	30.0	105.0	3.0	104.8
K110-10-10	良	30.0	1.0	30.7	20.0	1.0	20.3	82.0	2.5	82.0	24.0	1.0	24.3	102.0	3.0	102.3
K110-13-6	良	22.0	1.0	22.2	20.0	1.0	20.1	85.0	2.5	84.8	23.0	1.0	23.3	105.0	3.0	104.9
K110-13-6L	良	30.0	1.0	29.8	20.0	1.0	20.2	85.0	2.5	84.7	23.0	1.0	23.4	105.0	3.0	104.9
K110-13-13	良	30.0	1.0	30.7	20.0	1.0	20.2	84.0	2.5	83.9	23.0	1.0	23.0	104.0	3.0	104.1
K115-6-6H	良	25.0	1.0	24.8	17.0	0.5	16.5	93.0	3.0	92.6	27.0	1.0	26.2	110.0	3.0	109.1
K120-6-6H	良	25.0	1.0	24.8	17.0	0.5	16.5	98.0	3.0	97.6	27.0	1.0	26.5	115.0	3.0	114.1
K120-10-6H	良	30.0	1.0	30.5	16.0	0.5	15.6	99.0	3.0	98.9	30.0	1.0	29.9	115.0	3.0	114.5
K120-10-10	良	30.0	1.0	30.7	20.0	1.0	20.1	95.0	3.0	94.6	24.0	1.0	24.2	115.0	3.0	114.7
K120-13-10	良	22.5	1.0	22.8	15.0	0.5	14.5	95.0	3.0	96.3	41.5	2.0	41.4	110.0	3.0	110.8
K120-13-13	良	30.0	1.0	30.4	20.0	1.0	20.1	95.0	3.0	95.4	23.0	1.0	23.1	115.0	3.0	115.5
K125-4-4S	良	30.0	1.0	29.5	48.0	2.0	47.1	75.0	2.5	74.6	27.0	1.0	26.7	123.0	3.0	121.7
K125-10-6	良	30.0	1.0	29.9	20.0	1.0	19.4	100.0	3.0	100.1	23.0	1.0	22.8	120.0	3.0	119.5
K125-13-6	良	22.0	1.0	22.1	20.0	1.0	20.5	100.0	3.0	98.7	23.0	1.0	23.1	120.0	3.0	119.2
K125-13-6L	良	30.0	1.0	30.1	20.0	1.0	20.3	100.0	3.0	100.0	23.0	1.0	23.0	120.0	3.0	120.3
K130-10-10	良	30.0	1.0	30.0	20.0	1.0	20.2	105.0	3.0	105.9	25.0	1.0	24.4	125.0	3.0	126.1
K130-13-10	良	22.5	1.0	22.8	15.0	0.5	14.6	105.0	3.0	105.0	41.5	2.0	41.7	120.0	3.0	119.6
K130-13-13	良	30.0	1.0	30.2	20.0	1.0	19.9	105.0	3.0	105.6	23.0	1.0	23.3	125.0	3.0	125.5
K135-10-6H	良	30.0	1.0	30.3	16.0	0.5	15.7	114.0	3.0	113.5	30.0	1.0	29.6	130.0	3.0	129.2
K145-10-6H	良	30.0	1.0	29.6	16.0	0.5	15.7	124.0	3.0	123.4	30.0	1.0	29.7	140.0	3.0	139.1
K150-10-10	良	30.0	1.0	30.6	20.0	1.0	20.4	125.0	3.0	124.5	25.0	1.0	24.3	145.0	3.0	144.9
K150-13-10	良	22.5	1.0	22.5	15.0	0.5	14.6	125.0	3.0	126.7	41.5	2.0	41.6	140.0	3.0	141.3
K150-13-13	良	30.0	1.0	30.5	20.0	1.0	19.5	125.0	3.0	124.5	23.0	1.0	23.2	145.0	3.0	144.0